



Sturdo
RESTROOM CUBICLES & LOCKERS



Test Reports

ANTIVIRUS TEST REPORT



BIOTECH TESTING SERVICES

TEST REPORT

LAB NO. : 2002257/ 1 - 3

DATE: 31/07/2020

NAME OF CUSTOMER : GREENLAM INDUSTRIES LIMITED
ADDRESS : Vill. Paterh Bhonku, PO Panjehra,
Teh. Nalagarh, Distt. Salon,
Himachal Pradesh – 174 101
REFERENCE : Your Letter Ref. Nil dated July 11, 2020
DATE OF RECEIPT : 11/07/2020
DATE OF INITIATION : 11/07/2020
DATE OF COMPLETION : 31/07/2020
SAMPLE DESCRIPTION : Laminate Sample specimen labeled as –

Sr. No.	Description
1.	Greenlam Safeguard Plus and Anti-Virus Compact Laminate 13.00 mm thickness Décor 113
2.	Greenlam Untreated Compact Laminate 13.00 mm thickness Décor 141
Untreated – Lab Control	

Name of Test:

Measurement of Antiviral activity on plastics and other non-porous surfaces

Name of Test Protocol:

ISO 21702: 2019*

Scope of Method:

This test specifies method for measuring antiviral activity on plastic and other non-porous surface of antiviral-treated products against specified virus. Due to individual sensitivities, the results of one test virus might not be applicable for other viruses.

*Modified method with use of MS2 virus

Page 1 of 4

• Samples are not drawn by the laboratory • Result relate only to the samples tested
• This report shall not be reproduced except in full without prior permission of this laboratory

104/105, Malwa, Patanwala Ind. Estate, L.B.S. Marg, Ghatkopar (W), Mumbai - 400086, INDIA • Tel. : +91-22-2500 2811, 2500 2812
Email : info@biotechts.in / report@biotechts.in / biotechtestingservices@gmail.com / shilpanair@biotechts.in



BIOTECH TESTING SERVICES

Test Microorganism Information:

MS2 Bacteriophage (MS2) is an RNA virus of the family Leviviridae. Escherichia coli 15597 are the hosts for bacteriophages. Due to its environmental resistance, MS2 bacteriophages are used as a surrogate virus (particularly in place of Picornaviruses such as Poliovirus and human Norovirus) in water quality and Antimicrobial studies.

Virus: MS2 Bacteriophage

Permissive Host Cell: Escherichia coli ATCC 15597

Experimental Details:

Test Carrier : Panel surface (50 mm x 50 mm) ; Pre-sterilized by UV light

Control Carrier : Panel pre sterilized (50 mm x 50 mm)

LDPE cover : LDPE film pre sterilized 40 mm x 40 mm

Virus : MS2 Bacteriophage; Inoculum volume 0.4 ml

Permissive Host Cell : Escherichia coli ATCC 15597

Contact Period : 2 hours and 24 hours

Neutralizer : DE broth

Medium : Trypticase soya agar

Incubation for survivors : 37°C for 3 days

Validation and Records:

Neutralizer Validation and Records:

Validation Test			
Test Organism	Exptl. Condition Control (A) (CFU/ ml)	Neutralizer Toxicity Control (B) (CFU/ ml)	Dilution-neutralization Control © (CFU/ ml)
MS2 Bacteriophage	50	52	58

Where –

A=No. of PFU/ml of Test organism in Experimental condition validation

B=No. of PFU/ml of Test organism in Neutralizer Toxicity validation

2002257/1-2
Page 2 of 4

- Samples are not drawn by the laboratory • Result relate only to the samples tested
- This report shall not be reproduced except in full without prior permission of this laboratory

Test Procedure:

Pre-sterilized samples were loaded with diluted viral suspension to 10^6 PFU/ ml. Virus suspension 0.4 ml was added to 50 mm x 50 mm of Test substrate. It was covered with 40 mm x 40 mm LDPE film. Following exposure time, Virus was eluted and neutralized by serial tenfold dilution and assayed to determined surviving Viruses in comparison with Control without test product in sq. cms. Virus assay was quantitative as Plaque forming unit (PFU) visible as area of Clearance.

Results:
A: 2 HOURS

Quantitative Assessment of Antiviral Activity – ISO 21702: 2019				
Untreated: Average no. of Plaques recovered at 0 hours (U_0): 6.00×10^4 PFU/sq cm.				Log = 4.77
Untreated: Average no. of Plaques recovered at 2 hours (U_t): 7.10×10^4 PFU/sq cm.				Log = 4.85
Sample Identification	Average No. of Plaques recovered from Treated (A_t)	Log of Plaques recovered from Treated (A_t)	Antiviral Activity (R) ($\text{Log } U_t - A_t$)	Virus Reduction Percentage
Greenlam Safeguard Plus and Anti-Virus Compact Laminate 13.00 mm thickness Décor 113	620	2.79	2.06	99.12
Greenlam Untreated Compact Laminate 13.00 mm thickness Décor 141	7300	3.86	0.99	89.71

B: 24 HOURS

Quantitative Assessment of Antiviral Activity – ISO 21702: 2019				
Untreated: Average no. of Plaques recovered at 0 hours (U_0): 6.00×10^4 PFU/sq cm.				Log = 4.77
Untreated: Average no. of Plaques recovered at 24 hours (U_t): 9.00×10^4 PFU/sq cm.				Log = 4.95
Sample Identification	Average No. of Plaques recovered from Treated (A_t)	Log of Plaques recovered from Treated (A_t)	Antiviral Activity (R) ($\text{Log } U_t - A_t$)	Virus Reduction Percentage
Greenlam Safeguard Plus and Anti-Virus Compact Laminate 13.00 mm thickness Décor 113	90	1.95	3.00	99.90
Greenlam Untreated Compact Laminate 13.00 mm thickness Décor 141	1560	3.19	1.76	98.26

Where:

R = Antiviral activity

U_0 = Log of PFU recovered from Untreated specimen immediately after inoculation, in PFU/ cm^2

U_t = Log of PFU recovered from Untreated specimen after 2/ 24 hrs. after inoculation, in PFU/ cm^2

A_t = Log of PFU recovered from Treated specimen after 2/ 24 hrs. after inoculation, in PFU/ cm^2

COMMENT:

When tested as specified, laminate sample labeled as **Greenlam Safeguard Plus and Anti-Virus Compact Laminate 13.00 mm thickness Décor 113** has shown **99.12%** and **99.90%** Reduction; **Greenlam Untreated Compact Laminate 13.00 mm thickness Décor 141** has shown **89.71%** and **98.26%** Reduction of virus in 2 hours and 24 hours when tested by ISO 21702: 2019 standard.



For **BIOTECH TESTING SERVICES**



Dr Shilpa U. Nair
Quality Manager
(Authorized Signatory)

2002257/1-2
Page 4 of 4

• Samples are not drawn by the laboratory • Result relate only to the samples tested
• This report shall not be reproduced except in full without prior permission of this laboratory