



Sturdo
RESTROOM CUBICLES & LOCKERS



Test Reports

CHEMICAL RESISTANCE TEST REPORT

Test Report No. 7191010274-MEC11/-KSY
dated 13 JULY 2011



PSB Singapore

Note: This report is issued subject to TÜV SÜD PSB's "Terms and Conditions Governing Technical Services".
The terms and conditions governing the issue of this report are set out as attached within this report.

**Choose certainty.
Add value.**

SUBJECT:

Chemical Spot Test of High-Pressure Laminates

TESTED FOR:

Greenlam Asia Pacific Pte Ltd
18 Sungei Kadut Street 2
Singapore 729236

Attn: Ms Lin Hui Ping

SAMPLES DESCRIPTION:

Six pieces of 305 mm x 305 mm x 13 mm high pressure laminate test specimens (as shown in Figure 1) were submitted by Greenply Industries Ltd on 16 June 2011 for testing.



Figure 1a: Top View



Figure 1b: Bottom View



Laboratory:
TÜV SÜD PSB Pte. Ltd.
No.1 Science Park Drive
Singapore 118221

Phone : +65-6885 1333
Fax : +65-6776 8670
E-mail: testing@tuv-sud-psb.sg
www.tuv-sud-psb.sg
Co. Reg : 199002667R

Regional Head Office:
TÜV SÜD Asia Pacific Pte. Ltd.
3 Science Park Drive, #04-01/05
The Franklin, Singapore 118223
TUV®

Test Report No. 7191010274-MEC11-KSY
dated 13 JULY 2011



PSB Singapore

TEST METHOD: (AS SPECIFIED AND AGREED BY THE CLIENT)

SEFA – 1999 Laboratory Furniture Casework, Shelving and Tables Recommended Practices
Clause 8.1 - Chemical Spot Test

Nominal specimen dimensions : as received
 Reagents : Acids, Solvents, Bases, General Reagents, Stains and Indicators
 Test condition : 23 ± 2 °C for 16 h
 Observation : By visual method

TEST RESULTS:

Reagents	Observation	Level
A. Acids		
1. 20% Nitric Acid	No detectable change	0
2. 30% Nitric Acid	No detectable change	0
3. 65% Nitric Acid	No detectable change	0
4. 99% Glacial Acetic Acid	No detectable change	0
5. 33% Sulphuric Acid	No detectable change	0
6. 77% Sulphuric Acid	No detectable change	0
7. 96% Sulphuric	No detectable change	0
8. 37% Hydrochloric Acid	No detectable change	0
9. 85% phosphoric Acid	No detectable change	0
10. 90% Formic Acid	No detectable change	0
11. 48% Hydrofluoric Acid	No detectable change	0
12. Aqua Regia, 77% Sulphuric Acid & 65% Nitric Acid equal parts	No detectable change	0
13. 60% Chromic Trioxide (Chromic Acid Cleaning Solution)	No detectable change	0
14. 60% Perchloric Acid	Severe staining	2
B. Solvents		
1. Carbon Tetrachloride	No detectable change	0
2. Acetone	No detectable change	0
3. 37% Formaldehyde	No detectable change	0
4. Methanol	No detectable change	0
5. Ethyl Acetate	No detectable change	0
6. Toluene	No detectable change	0
7. N-hexane	No detectable change	0
8. Ethyl Alcohol	No detectable change	0
9. Chloroform	No detectable change	0
10. 80% Phenol Solution	No detectable change	0
11. Xylene	No detectable change	0
12. Amyl Acetate	No detectable change	0
13. Dimethylformamide	No detectable change	0
14. Methylene Chloride	No detectable change	0
15. Methyl Ethyl Ketone	No detectable change	0
16. Tetrahydrofuran	No detectable change	0



TEST RESULTS (CONT'D):

Reagents	Observation	Level
C. Bases		
1. 10% Sodium Hydroxide	No detectable change	0
2. 20% Sodium Hydroxide	No detectable change	0
3. 40% Sodium Hydroxide	No detectable change	0
4. Sodium Hydroxide Flakes	No detectable change	0
5. 25% Ammonium Hydroxide	No detectable change	0
D. General Reagents		
1. 5% Sodium Hypochloride	No detectable change	0
2. 3% Hydrogen Peroxide	No detectable change	0
3. 30% Trisodium Phosphate	No detectable change	0
4. Zinc Chloride (saturated solution)	No detectable change	0
5. Gasoline	No detectable change	0
6. Kerosene	No detectable change	0
7. Mineral Oil	No detectable change	0
8. Vegetable Oil (Olive)	No detectable change	0
9. Water	No detectable change	0
10. 0.1% Potassium Permanganate	Slight change in color / gloss	1
11. 5% Silver Nitrite	Slight change in color / gloss	1
12. 5% Copper Sulphate	No detectable change	0
13. Ethylene Glycol	No detectable change	0
14. Karl Fischer Reagent	No detectable change	0
15. 5% Urea	No detectable change	0
16. 5% Ferric Sulphate	No detectable change	0
E. Stains and Indicators		
1. 0.1% Phenolphthalein	No detectable change	0
2. 0.1% Methyl Red	No detectable change	0
3. 1% Gentian Violet	Slight change in color / gloss	1
4. 0.1% Methylene Blue	No detectable change	0
5. 0.1% Crystal Violet	No detectable change	0
6. 0.1% Malachite Green	Severe staining	2
7. 0.1% Thymol Blue	No detectable change	0

NOTES:

Level 0 - No detectable change.

Level 1 - Slight change in color or gloss.

Level 2 - Slight surface etching or severe staining.

Level 3 - Pitting, Cratering, swelling, or erosion of coating, obvious and significant deterioration.

Kong Siew Yong
Associate Engineer

Li Xiang
Engineer
Polymer Products
Mechanical Centre

Test Report No. 7191010274-MEC11-KSY
dated 13 JULY 2011



PSB Singapore

This Report is issued under the following conditions:

1. Results of the testing/calibration in the form of a report will be issued immediately after the service has been completed or terminated.
2. Unless otherwise requested, this report shall contain only technical results carried out by TÜV SÜD PSB. Analysis and interpretation of the results and professional opinion and recommendations expressed thereupon, if required, shall be clearly indicated and additional fee paid for, by the Client.
3. This report applies to the sample of the specific product/equipment given at the time of its testing/calibration. The results are not used to indicate or imply that they are applicable to other similar items. In addition, such results must not be used to indicate or imply that TÜV SÜD PSB approves, recommends or endorses the manufacturer, supplier or user of such product/equipment, or that TÜV SÜD PSB in any way "guarantees" the later performance of the product/equipment. Unless otherwise stated in this report, no tests were conducted to determine long term effects of using the specific product/equipment.
4. The sample/s mentioned in this report is/are submitted/supplied/manufactured by the Client. TÜV SÜD PSB therefore assumes no responsibility for the accuracy of information on the brand name, model number, origin of manufacture, consignment or any information supplied.
5. Additional copies of the report are available to the Client at an additional fee. No third party can obtain a copy of this report through TÜV SÜD PSB, unless the Client has authorised TÜV SÜD PSB in writing to do so.
6. TÜV SÜD PSB may at its sole discretion add to or amend the conditions of the report at the time of issue of the report and such report and such additions or amendments shall be binding on the Client.
7. All copyright in the report shall remain with TÜV SÜD PSB and the Client shall, upon payment of TÜV SÜD PSB's fees for the carrying out of the tests/calibrations, be granted a license to use or publish the report to the third parties subject to the terms and conditions herein, provided always that TÜV SÜD PSB may at its absolute discretion be entitled to impose such conditions on the license as it sees fit.
8. Nothing in this report shall be interpreted to mean that TÜV SÜD PSB has verified or ascertained any endorsement or marks from any other testing authority or bodies that may be found on that sample.
9. This report shall not be reproduced wholly or in parts and no reference shall be made by the Client to TÜV SÜD PSB or to the report or results furnished by TÜV SÜD PSB in any advertisements or sales promotion.
10. Unless otherwise stated, the tests were carried out in TÜV SÜD PSB Pte Ltd, No.1 Science Park Drive Singapore 118221.

March 2010